


TECHNICAL DATASHEET

Rocko - 5 mm

Flooring for floating installation, Level of use according to EN 16511: Class 34



For intensively used living areas



For flooring subject to intensive use in commercial premises



DIMENSIONS

dimensions	thickness	5,0 mm · tmax - tmin ≤ 0,50 mm	
	length	600 mm · lmax - lmin ≤ 0,50 mm	
	width	295 ± 0,10 mm · wmax - wmin ≤ 0,20 mm	
profile	long side	1 clic 2go pure	short side 1 clic 2go pure
groove	long side		short side

TOLERANCE

squareness	EN 16511	≤ 0,20 mm
straightness	EN 16511	≤ 0,30 mm / m
flatness crosswise	EN 16511	concave: ≤ 0,15% · convex: ≤ 0,20%
flatness lengthwise	EN 16511	concave: ≤ 0,50% · convex: ≤ 1,00%
openings between elements	EN 16511	average: ≤ 0,15 mm · max: ≤ 0,20 mm
height difference between elements	EN 16511	average: ≤ 0,10 mm · max: ≤ 0,15 mm

TEST

abrasion resistance method B	EN 16511	≥ 7000 cycles
impact resistance	EN 16511	≥ 1800 mm
micro scratch resistance	EN 16511	≤ MSR-A2
stain resistance	group 1 & 2	grade 5
	group 3	grade 5
castor chair test	EN 16511	no change in appearance after 25.000 cycles
effect of furniture leg	EN 16511	no visible damage
thickness swelling	EN 16511	no swelling
residual indentation	EN 16511	≤ 0,15mm
light fastness	EN 20105-B02	blue wool scale 6
	EN 20105-A02	grey scale ≥ 4
locking strength	EN 16511	long side ≥ 2,0 kN/m
		short side ≥ 3,5 kN/m
dimensional stability	EN 16511	≤ 0,25 %

ENVIRONMENT

emission of formaldehyde	EN 717-1	class E1, formaldehyde free, no emission
--------------------------	----------	--

PHYSICAL BEHAVIOR

fire behaviour	EN 13501-1	Bfl-s1
slide resistance	EN 13893	DS
thermal resistance	EN 12667	0,01 (m²K)/W
thermal conductivity	EN 12667	0,437 W/(m*K)
walking noise reduction	IHD-W-431	37%
impact sound reduction	EN ISO 10140-3	6 dB

The data sheet is updated regularly to meet new technological standards.
This version replaces all previous versions as well as those which are undated.
This version takes effect upon creation. Version 01/2019


TECHNICAL DATASHEET

Rocko - 5 mm

Flooring for floating installation, Level of use according to EN 16511: Class 34



For intensively used living areas



For flooring subject to intensive use in commercial premises



DIMENSIONS

dimensions	thickness	5,0 mm · tmax - tmin ≤ 0,50 mm	
	length	1210 mm · lmax - lmin ≤ 0,50 mm	
	width	192 ± 0,10 mm · wmax - wmin ≤ 0,20 mm	
profile	long side	1 clic 2go pure	short side 1 clic 2go pure
groove	long side		short side

TOLERANCE

squareness	EN 16511	≤ 0,20 mm
straightness	EN 16511	≤ 0,30 mm / m
flatness crosswise	EN 16511	concave: ≤ 0,15% · convex: ≤ 0,20%
flatness lengthwise	EN 16511	concave: ≤ 0,50% · convex: ≤ 1,00%
openings between elements	EN 16511	average: ≤ 0,15 mm · max: ≤ 0,20 mm
height difference between elements	EN 16511	average: ≤ 0,10 mm · max: ≤ 0,15 mm

TEST

abrasion resistance method B	EN 16511	≥ 7000 cycles
impact resistance	EN 16511	≥ 1800 mm
micro scratch resistance	EN 16511	≤ MSR-A2
stain resistance	group 1 & 2	grade 5
	group 3	grade 5
castor chair test	EN 16511	no change in appearance after 25.000 cycles
effect of furniture leg	EN 16511	no visible damage
thickness swelling	EN 16511	no swelling
residual indentation	EN 16511	≤ 0,15mm
light fastness	EN 20105-B02	blue wool scale 6
	EN 20105-A02	grey scale ≥ 4
locking strength	EN 16511	long side ≥ 2,0 kN/m
		short side ≥ 3,5 kN/m
dimensional stability	EN 16511	≤ 0,25 %

ENVIRONMENT

emission of formaldehyde	EN 717-1	class E1, formaldehyde free, no emission
--------------------------	----------	--

PHYSICAL BEHAVIOR

fire behaviour	EN 13501-1	Bfl-s1
slide resistance	EN 13893	DS
thermal resistance	EN 12667	0,01 (m²K)/W
thermal conductivity	EN 12667	0,437 W/(m*K)
walking noise reduction	IHD-W-431	37%
impact sound reduction	EN ISO 10140-3	6 dB

The data sheet is updated regularly to meet new technological standards.
This version replaces all previous versions as well as those which are undated.
This version takes effect upon creation. Version 01/2019

kronospan

Kronoflooring Sp. z o.o.,
38-200 Jasło, ul. Przemysłowa 10, Poland


TECHNICAL DATASHEET

Rocko - 5 mm

Flooring for floating installation, Level of use according to EN 16511: Class 34



For intensively used living areas



For flooring subject to intensive use in commercial premises



DIMENSIONS

dimensions	thickness	5,0 mm · tmax - tmin ≤ 0,50 mm	
	length	1210 mm · lmax - lmin ≤ 0,50 mm	
	width	234 ± 0,10 mm · wmax - wmin ≤ 0,20 mm	
profile	long side	1 clic 2go pure	short side 1 clic 2go pure
groove	long side		short side

TOLERANCE

squareness	EN 16511	≤ 0,20 mm
straightness	EN 16511	≤ 0,30 mm / m
flatness crosswise	EN 16511	concave: ≤ 0,15% · convex: ≤ 0,20%
flatness lengthwise	EN 16511	concave: ≤ 0,50% · convex: ≤ 1,00%
openings between elements	EN 16511	average: ≤ 0,15 mm · max: ≤ 0,20 mm
height difference between elements	EN 16511	average: ≤ 0,10 mm · max: ≤ 0,15 mm

TEST

abrasion resistance method B	EN 16511	≥ 7000 cycles
impact resistance	EN 16511	≥ 1800 mm
micro scratch resistance	EN 16511	≤ MSR-A2
stain resistance	group 1 & 2	grade 5
	group 3	grade 5
castor chair test	EN 16511	no change in appearance after 25.000 cycles
effect of furniture leg	EN 16511	no visible damage
thickness swelling	EN 16511	no swelling
residual indentation	EN 16511	≤ 0,15mm
light fastness	EN 20105-B02	blue wool scale 6
	EN 20105-A02	grey scale ≥ 4
locking strength	EN 16511	long side ≥ 2,0 kN/m
		short side ≥ 3,5 kN/m
dimensional stability	EN 16511	≤ 0,25 %

ENVIRONMENT

emission of formaldehyde	EN 717-1	class E1, formaldehyde free, no emission
--------------------------	----------	--

PHYSICAL BEHAVIOR

fire behaviour	EN 13501-1	Bfl-s1
slide resistance	EN 13893	DS
thermal resistance	EN 12667	0,01 (m²K)/W
thermal conductivity	EN 12667	0,437 W/(m*K)
walking noise reduction	IHD-W-431	37%
impact sound reduction	EN ISO 10140-3	6 dB

The data sheet is updated regularly to meet new technological standards.
This version replaces all previous versions as well as those which are undated.
This version takes effect upon creation. Version 01/2019

kronospan

Kronoflooring Sp. z o.o.,
38-200 Jasło, ul. Przemysłowa 10, Poland


TECHNICAL DATASHEET

Rocko - 5 mm

Flooring for floating installation, Level of use according to EN 16511: Class 34



For intensively used living areas



For flooring subject to intensive use in commercial premises



DIMENSIONS

dimensions	thickness	5,0 mm · tmax - tmin ≤ 0,50 mm	
	length	1210 mm · lmax - lmin ≤ 0,50 mm	
	width	295 ± 0,10 mm · wmax - wmin ≤ 0,20 mm	
profile	long side	1 clic 2go pure	short side 1 clic 2go pure
groove	long side		short side

TOLERANCE

squareness	EN 16511	≤ 0,20 mm
straightness	EN 16511	≤ 0,30 mm / m
flatness crosswise	EN 16511	concave: ≤ 0,15% · convex: ≤ 0,20%
flatness lengthwise	EN 16511	concave: ≤ 0,50% · convex: ≤ 1,00%
openings between elements	EN 16511	average: ≤ 0,15 mm · max: ≤ 0,20 mm
height difference between elements	EN 16511	average: ≤ 0,10 mm · max: ≤ 0,15 mm

TEST

abrasion resistance method B	EN 16511	≥ 7000 cycles
impact resistance	EN 16511	≥ 1800 mm
micro scratch resistance	EN 16511	≤ MSR-A2
stain resistance	group 1 & 2	grade 5
	group 3	grade 5
castor chair test	EN 16511	no change in appearance after 25.000 cycles
effect of furniture leg	EN 16511	no visible damage
thickness swelling	EN 16511	no swelling
residual indentation	EN 16511	≤ 0,15mm
light fastness	EN 20105-B02	blue wool scale 6
	EN 20105-A02	grey scale ≥ 4
locking strength	EN 16511	long side ≥ 2,0 kN/m
		short side ≥ 3,5 kN/m
dimensional stability	EN 16511	≤ 0,25 %

ENVIRONMENT

emission of formaldehyde	EN 717-1	class E1, formaldehyde free, no emission
--------------------------	----------	--

PHYSICAL BEHAVIOR

fire behaviour	EN 13501-1	Bfl-s1
slide resistance	EN 13893	DS
thermal resistance	EN 12667	0,01 (m²K)/W
thermal conductivity	EN 12667	0,437 W/(m*K)
walking noise reduction	IHD-W-431	37%
impact sound reduction	EN ISO 10140-3	6 dB

The data sheet is updated regularly to meet new technological standards.
This version replaces all previous versions as well as those which are undated.
This version takes effect upon creation. Version 01/2019

kronospan

Kronoflooring Sp. z o.o.,
38-200 Jasło, ul. Przemysłowa 10, Poland